














Tile performance data - notes techniques - technische auskünfte - техническая характеристика

Classificazione secondo EN ISO 14411 ISO 13006 annesso G gruppo B1A con E ≤0,5% - Classification in accordance with EN ISO 14411 ISO 13006 annex G standards B1A with E ≤ 0,5%
 Classification selon EN ISO 14411 ISO 13006 annexe G groupe B1A avec E ≤0,5% - Klassifizierung gemäß EN ISO 14411 ISO 13006 anlage G Gruppe B1A mit E ≤0,5%
 Классификация в соответствии с EN ISO 14411 ISO 13006, приложение G, стандарт B1A, где E ≤0,5%

	CARATTERISTICA TECNICA TECHNICAL CHARACTERISTIC CARACTERISTIQUE TECHNIQUE TECHNISCHE DATEN ТЕХНИЧЕСКАЯ ХАРАКТЕРИСТИКА	NORMA NORMS NORME NORM НОРМА	VALORE * MEDIO "CAESAR" AVERAGE "CAESAR" VALUE * - VALEUR * MOYEN "CAESAR" "CAESAR" DURCHSCHNITTSWERT * - СРЕДНЕЕ ЗНАЧЕНИЕ "CAESAR" *		
			Autore / Built / Trace / One / Portraits / Core / Tecnolito / Relate / Be More / Tinte Unite Naturale - Matt - Naturel - Natur - Матовая	Anima / Anima Select Silk	Anima / Anima Select Lucidato GL
	Dimensione - Size Dimension - Abmessungen - Размер	ISO 10545-2	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует
	Assorbimento d'acqua* - Water absorption* Absorption d'eau* - Wasseraufnahme* - % Поглощения воды*	ISO 10545-3	≤ 0,1%	≤ 0,1%	≤ 0,1%
	Water absorption*	◆ ASTM C373-88 (2006)	In accordance	In accordance	In accordance
	Resistenza alla flessione* - Bending strength* Résistance à la flexion* - Biegezugfestigkeit* -Упругость*	ISO 10545-4	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует
	Resistenza all'urto - Impact resistance Résistance au choc - Schlagfestigkeit - Ударопрочность	ISO 10545-5	> 0,8	> 0,8	> 0,8
	Resistenza all'abrasione profonda* - Deep scratch resistance* Résistance à l'abrasion profonde* - Widerstand gegen Tiefenverschleiß* - Устойчивость глубокому истиранию*	ISO 10545-6	≤ 145 mm ³	≤ 145 mm ³	-
	Coefficiente di dilatazione termica lineare* Thermal linear expansion coefficient* - Coefficient de dilatation thermique linéaire* - Koeffizient der linearen thermischen Dehnung* - Коэффициент линейного теплового расширения*	ISO 10545-8	~ 7 (10 ⁻⁶ °C ⁻¹)	~ 7 (10 ⁻⁶ °C ⁻¹)	~ 7 (10 ⁻⁶ °C ⁻¹)
	Resistenza al cavillo - Crazing resistance Résistance aux craquelures - Haariß-Beständigkeit Устойчивость эмали к кракелюру	ISO 10545-11	-	-	Conforme - In accordance Conforme - Erfüllt - Соответствует
	Resistenza all'attacco chimico - Resistance to chemical attack Résistance à l'attaque chimique - Beständigkeit gegen Chemikalien Устойчивость к химическому воздействию	ISO 10545-13	Resistente - Resistant - Résistante Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий
	Resistenza alle macchie* - Resistance to stains* Résistance aux taches* - Fleckenbeständigkeit* Устойчивость к образованию пятен*	ISO 10545-14	Pulibile - Cleanable - Nettoyable Leicht zu reinigen - Чистящийся	Pulibile - Cleanable - Nettoyable - Leicht zu reinigen - Чистящийся	Pulibile - Cleanable - Nettoyable - Leicht zu reinigen - Чистящийся
	Resistenza allo scivolamento** Slip resistance** Résistance au glissement** Rutschhemmende Eigenschaft** Сопротивление скольжению**	DIN 51130	Trace = R9 A One = R9 A BeMore = R10 A Portraits = R9 Autore = R9 Core = R10 A+B Tecnolito = R9 Anima = R9 Relate = R10 A Built = R10 A Anima Select = R9		
		▲ DCOF	Conforme - In accordance - Conforme Erfüllt - Соответствует		
	Resistenza all'abrasione superficiale Surface abrasion resistance Résistance à l'abrasion superficielle Widerstand gegen Oberflächenverschleiß Сопротивление на изгиб и усилию на излом	EN ISO 10545-7	-		Test disponibili in azienda Tests available at our company Tests disponibles en usine Prüfzeugnisse beim Werk erhältlich - Протоколы испытаний хранятся в компании
	Spessore nominale - Nominal Thickness Épaisseur nominale - Nominalstärke - Номинальная толщина		160x160 - 160x320 - 119,5x278 = 6 mm 119,5x119,5 - 119,5x239 = 9 mm	160x160 - 160x320 = 6 mm	160x160 - 160x320 119,5x278 = 6 mm 119,5x119,5 - 119,5x239 = 9 mm

* Valori medi riferiti agli ultimi due anni di produzione e relativi alla finitura naturale del prodotto - Average values referred to the last two years of production and related to the matt finish of the product - Valeurs moyennes des deux dernières années de production et relatifs à la finition naturelle du produit - Durchschnittswerte, die sich auf die letzten zwei Produktionsjahre beziehen und auf die matte Oberfläche - Средние значения относятся к последним двум годам производства и натуральной отделке поверхности.

** Valori relativi alla finitura naturale del prodotto ed a test effettuati da laboratori esterni accreditati, disponibili in azienda; ci rendiamo disponibili alla verifica dell'eventuale lotto interessato all'acquisto.
 As far as values relating to the matt finish of the product and to tests carried out by certified external laboratories whose results are available upon request at Headoffice, we are willing to check the lot you are interested in purchasing.
 Valeurs se référant à la finition naturelle du produit selon des tests effectués par des laboratoires extérieurs accrédités et à la disposition de toute personne intéressée auprès de nos bureaux; nous sommes disponibles pour le contrôle de l'éventuel lot concerné par l'achat. - Werte bezogen auf das natürliche Produktfinish und in anerkannten externen Labors geprüft, im Unternehmen erhältlich; für eventuelle Prüfungen der zu erwerbenden Warenposten stehen wir gern zur Verfügung. - Значения, касающиеся натуральных характеристик изделий и тестов, выполненных внешними авторизованными лабораториями, имеются компании. Мы готовы выполнить проверку партии товара, которую намереваетесь приобрести.

• Per prodotti chimici di uso domestico e additivi per piscina - For domestic chemicals and swimming pool additives - Pour produits chimiques à usage domestique et additifs pour piscines - Für chemische Produkte für den Hausgebrauch und Schwimmbadzusätze - Для бытовых химикатов и добавок для бассейнов.

▲ Valore minimo richiesto ANSI A137.1 - 2012 > 0,42 - Minimum Value Required ANSI A137.1 - 2012 > 0,42 - Valeur Minimum Demandée ANSI A137.1 - 2012 > 0,42 - Erforderlicher Mindestwert ANSI A137.1 - 2012 > 0,42 - Минимальное требуемое значение по ANSI A137.1-2012 >0,42

◆ Valore richiesto ANSI A137.1-2012 WA ≤ 0,5% - Value Required ANSI A137.1-2012 WA ≤ 0,5% - Valeur Demandée ANSI A137.1-2012 WA ≤ 0,5% - Erforderlicher Wert ANSI A137.1-2012 WA ≤ 0,5% - Требуемое значение ANSI A137.1 2012 WA ≤ 0,5%

Le tonalità dei campioni sono da considerarsi puramente indicative - Tones of samples are indicative - Les tonalités des échantillons sont purement indicatives - Die farbtöne der Muster sind als rein indicativ zu betrachten
 Тона образцов ориентировочные.