

NOTES TECHNIQUES - TECHNISCHE AUSKÜNFTE - ТЕХНИЧЕСКАЯ ХАРАКТЕРИСТИКА

Classificazione secondo EN ISO 14411 ISO 13006 annesso G gruppo B1A con E ≤0,5% - Classification in accordance with EN ISO 14411 ISO 13006 annex G standards B1A with E ≤ 0,5%
Classification selon EN ISO 14411 ISO 13006 annexe G groupe B1A avec E ≤0,5% - Klassifizierung gemäß EN ISO 14411 ISO 13006 anlage G Gruppe B1A mit E ≤0,5%
Классификация в соответствии с EN ISO 14411 ISO 13006, приложение G, стандарт B1A, где E ≤0,5%

	CARATTERISTICA TECNICA TILE PERFORMANCE DATA CARACTERISTIQUE TECHNIQUE TECHNISCHE DATEN ТЕХНИЧЕСКАЯ ХАРАКТЕРИСТИКА	NORMA NORMS NORME NORM НОРМА	VALORE * MEDIO "CAESAR" AVERAGE "CAESAR" VALUE * VALEUR * MOYEN "CAESAR" "CAESAR" DURCHSCHNITTSWERT * СРЕДНЕЕ ЗНАЧЕНИЕ "CAESAR" *	VALORE * MEDIO "CAESAR" AVERAGE "CAESAR" VALUE * VALEUR * MOYEN "CAESAR" "CAESAR" DURCHSCHNITTSWERT * СРЕДНЕЕ ЗНАЧЕНИЕ "CAESAR" *	A E X T R A 2 0 OPEN YOUR STYLE
	Dimensione - Size Dimension - Abmessungen Размер	ISO 10545-2	Conforme - In accordance	Conforme - In accordance	
	Assorbimento d'acqua* - Water absorption* Absorption d'eau* - Wasseraufnahme* - % Поглощения воды*	ISO 10545-3	≤ 0,1%	≤ 0,1%	
	Water absorption*	♦ASTM C373-88 (2006)	In accordance	In accordance	
	Resistenza alla flessione* - Bending strength* Résistance à la flexion* - Biegezugfestigkeit* - Упругость*	ISO 10545-4	≤ 47 N / mm ²	Non applicabile a piastrelle con una forza di rottura ≥ 3000 N Not applicable to tiles with a breaking strength ≥ 3000 N N'est pas applicable aux carreaux avec une charge de rupture ≥ 3000 N Nicht anwendbar bei Fliesen mit einer Bruchlast ≥ 3000 N Не применяется в отношении плиток с прочностью на разрыв 3000 N	
	Sforzo di rottura (S) - Breaking strength Charge de rupture - Bruchlast - Разрушающее усилие	ISO 10545-4	Sps ≥ 7,5 mm S ≥ 1300 N	> 10.000 N	
	Resistenza all'abrasione profonda* - Deep scratch resistance* Résistance à l'abrasion profonde* - Widerstand gegen Tiefenverschleiß* Устойчивость глубокому истиранию*	ISO 10545-6	≤ 145 mm ³	≤ 145 mm ³	
	Coefficiente di dilatazione termica lineare* Thermal linear expansion coefficient* Coefficient de dilatation thermique linéaire* Koeffizient der linearen thermischen Dehnung* Кoeffициент линейного температурного	ISO 10545-8	≈ 7 (10 ⁻⁶ °C ⁻¹)	≈ 7 (10 ⁻⁶ °C ⁻¹)	
	Resistenza agli sbalzi termici* - Thermal shock resistance* Résistance aux écarts de température* - Temperaturwechsel Beständigkeit* Устойчивость к температурному перепаду*	ISO 10545-9	Resistente - Resistant Résistante - Beständig Стойкий	Resistente - Resistant Résistante - Beständig Стойкий	
	Dilatazione all'umidità* - Expansion in humidity* Dilatation à l'humidité* - Feuchtigkeitssausdehnung* Расширение в условиях влажности*	ISO 10545-10	≤ 0,1 (mm/m)	≤ 0,1 (mm/m)	
	Resistenza al gelo* - Frost resistance Résistance au gel - Frostbeständigkeit Морозоустойчивость*	ISO 10545-12	Resistente - Resistant Résistante - Beständig Стойкий	Resistente - Resistant Résistante - Beständig Стойкий	
	Resistenza all'attacco chimico • - Resistance to chemical attack • Résistance à l'attaque chimique • - Beständigkeit gegen Chemikalien • Устойчивость к химическому воздействию •	ISO 10545-13	Resistente - Resistant Résistante - Beständig Стойкий	Resistente - Resistant Résistante - Beständig Стойкий	
	Carico statico - Static load Charge statique - Statische Last - Статическая нагрузка	EN 12825	-		60x60 Centro - Centre - Au centre - Mitte - По центру KN>7,0 Centro lato - Side centre - Au centre latérallement - Mitte Seite - По центру грани KN>5,0 Diagonale - Diagonal - En diagonale - Diagonal - По диагонали KN>8,0
	Classe di carico di rottura Breaking load class - Classe de charge de rupture Bruchlastklasse - Класс стойкости к разрушающей нагрузке	EN 1339	-	U11*** T11***	
	Resistenza alle macchie* - Resistance to stains* Résistance aux taches* - Fleckenbeständigkeit* - Устойчивость к образованию пятен*	ISO 10545-14	Pulibile - Cleanable Nettoyable - Leicht zu reinigen Чистящийся	Pulibile - Cleanable Nettoyable - Leicht zu reinigen Чистящийся	
	Resistenza allo scivolamento** - Slip resistance** Résistance au glissement** - Rutschhemmende Eigenschaft** Спротивление скольжению**	DIN 51130-51097 ▲ DCOF	Naturale - Matt - Naturel - Natur - Матовая Grip R10 A R11 A+B+C Conforme - In accordance	R11 A+B+C Conforme - In accordance	
	Spessore nominale - Nominal Thickness Épaisseur nominale - Nominalstärke Номинальная толщина		30x120 - 20x120 - 60x60 - 30x60 7,5x30 9,5 mm 8,5 mm	20 mm	

* Valori medi riferiti agli ultimi due anni di produzione. - Average values referred to the last two years of production. - Valeurs moyennes des deux dernières années de production. - Durchschnittswerte, die sich auf die letzten zwei Produktionsjahre beziehen. - Средние значения относятся к последним двум годам производства и натуральной отделке поверхности.

** Valori relativi alla finitura naturale del prodotto ed a test effettuati da laboratori esterni accreditati, disponibili in azienda; ci rendiamo disponibili alla verifica dell'eventuale lotto interessato all'acquisto. As far as values relating to the matt finish of the product and to tests carried out by certified external laboratories whose results are available upon request at Headoffice, we are willing to check the lot you are interested in purchasing. - Valeurs se référant à la finition naturelle du produit selon des tests effectués par des laboratoires extérieurs accrédités et à la disposition de toute personne intéressée auprès de nos bureaux; nous sommes disponibles pour le contrôle de l'éventuel lot concerné par l'achat. - Werte bezogen auf das natürliche Produktfinish und in anerkannten externen Labors geprüft, im Unternehmen erhältlich; für eventuelle Prüfungen der zu erwerbenden Warenposten stehen wir gern zur Verfügung. - Значения, касающиеся натуральных характеристик изделий и тестов, выполненных внешними авторизованными лабораториями, имеются компании. Мы готовы выполнить проверку партии товара, которую намереваетесь приобрести.

*** Dato riferito al formato 60x60 cm. - Detail referred to the 60x60 cm size. - Donnée se rapportant au format 60x60 cm. - Auf die Formate 60x60 cm bezogen. - Значения, касающиеся натуральных характеристик изделий и тестов.

• Per prodotti chimici di uso domestico e additivi per piscina. - For domestic chemicals and swimming pool additives. - Pour produits chimiques à usage domestique et additifs pour piscines. - Für chemische Produkte für den Hausgebrauch und Schwimmbadzusätze. - Для бытовых химикатов и добавок для бассейнов.

▲ Valore minimo richiesto ANSI A137.1 - 2012 > 0,42. - Minimum Value Required ANSI A137.1 - 2012 > 0,42. - Valeur Minimum Demandée ANSI A137.1 - 2012 > 0,42. - Erforderlicher Mindestwert ANSI A137.1 - 2012 > 0,42. - Минимальное требуемое значение по ANSI A137.1-2012 >0,42.

♦ Valore richiesto ANSI A137.1-2012 WA ≤ 0,5%. - Value Required ANSI A137.1-2012 WA ≤ 0,5%. - Valeur Demandée ANSI A137.1-2012 WA ≤ 0,5%. - Erforderlicher Wert ANSI A137.1-2012 WA ≤ 0,5%. - Требуемое значение ANSI A137.1 2012 WA ≤ 0,5%.